Low Charging Clear Zipper Overall Width (OW) STATSHIELD® ESD Shielding Bag Contents Metal In Construction Static Sancitive Handling Precautions Required Length (L) Made in America (PQ) Lead-free RoHS compliant Bag Date & Lot Code Printed for QC Traceablility Weld Weld

Side Weld Seals 3/8 in. (±0.10)

Soft Fold Bottom



Specifications:

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20) ANSI/ESD S11.4

Electrical Properties

Surface Resistance: Outer Surface Inner Surface Discharge Shielding Charge Generation

Capacitance Probe (to dissipate 1 KV)

Typical Values

 1×10^4 to $< 1 \times 10^{11}$ ohms $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ <20 nJ

Teflon: 0.09 nC/sq. in. Quartz: 0.01 nC/sq. in.

Nominal -0" / + 0.125"

Nominal ± 0.125"

4600 PSI, 32 MPa

>40% (Tobias)

>10 lbs/in

Not detected

>10 lbs

Pass

<30 volts

Meets Requirements of:

ESD Protective Packaging Level 3 Technical Requirements

Test Procedures/Method

ANSI/ESD STM11.11 ANSI/ESD STM11.11 ANSI/ESD STM11.31, EIA 541 Modified Incline Plane

Modified Incline Plane

ANSI/EIA-541/Appendix E, 1kV Discharge

Nominal 0.0030" (0.0762mm) ±10% MIL-STD-3010, 1003

ASTM D-1003 375°F, 1/2 sec 60 psi **ASTM 882**

MIL-STD-3010, 2065 FTIR

IPC-TM-650 2.4.1

Physical Properties

Film Thickness Width (Inside Dimensions) Length (Inside Dimensions) Light Transmission Heat Seal Tensile Strength Puncture Resistance Silicone

Marking Adhesion

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS 2, REACH and Conflict Minerals Statement

None of the RoHS 2 restricted materials, REACH substances of very high concern as of 2016/06/20, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Desco Industries Inc. Limited Warranty at Desco.com.

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE



Specifications and procedures subject to change without notice.

STATSHIELD® BAG. SHIELDING. METAL-IN CONSTRUCTION. ZIPPER. 0.0030" (0.0762mm)



Statshield® bags are packaged 100 per package in an oversized shielding bag.

Mixed Unsortable Plastic Scrap Mixed unsortable plastic scrap shall contain assorted plastics

of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

DRAWING NUMBER 13605

DATE: August 2016

Low Charging Static

Low Charging Static

Dissipative Proprietary

Inner Polvethylene Laver

See Shielding Bag Storage at TB-7507.

Dissipative Proprietary Outer Polyester Layer Aluminum Shielding Layer