

Product Information

C/D Solv™ RE

Rapidly Evaporating Cleaner/Degreaser **3040**

Introduction

C/D-Solv[™] RE is a rapidly evaporating alternative to chlorinated solvent cleaning. C/D/ is a rapidly penetrating formulation that minimizes equipment maintenance time. This non-ozone depleting formula does not contain CFCs, 1,1,1-trichloroethane, or other chlorinated solvents. C/D-Solv[™] RE is safe on metals and most plastics.

Features / Benefits Rapidly Evaporating Safe on Most Plastics Non-Ozone Depleting Residue Free Rapidly Penetrating Non-Corrosive

| Physical Properties | | |
|--------------------------|---------------|--|
| Boiling Point | 149°C / 300°F | |
| Flash Point (TCC) | -17°C / 2°F | |
| Evaporation Rate | NIF | |
| Surface Tension | 21 | |
| Kauri-Butanol (KB Value) | 96.8 | |

Chemical Components

| Heptane | (142-82-5) | 44-50% |
|-------------------------------------|------------|--------|
| Acetone | , , | 40-45% |
| Naphtha C5-C6 | , | 10-15% |
| n-Pentyl acetate | , | 1-2% |
| 2-Methyl butyl acetate | | 1-2% |
| Carbon Dioxide (Aerosol Propellant) | | 1-5% |

Plastic Compatibility

| Material | Compatibility | Material | Compatibility |
|----------|----------------|----------|----------------|
| ABS | Excellent | PMMA | Not Compatible |
| Nylon 6 | Excellent | POM | Excellent |
| Lexan | Not Compatible | PP | Excellent |
| HDPE | Excellent | PS | Not Compatible |
| LDPE | Excellent | PTFE | Excellent |
| Phenolic | Excellent | PVC | Excellent |

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Packaging and Availability

C/D Solv™ RE is available in the following sizes:

3040-13S 13 Ounce Aerosol 3040-5G 30 Pounds in Metal 3040-55G 305 Pounds in Metal

Resources

Techspray® products are supported by a global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

North America Tech Spray L.P. P.O. Box 949 Amarillo, TX 79105 800-858-4043

enray com

email: tsales@techspray.com

Europe Techspray International UNIT 4, 44/46 Bunyan Road, Kempston Bedford MK42 8HL United Kingdom +44 (0) 1234 855443

email: tseurope@techspray.com

Countries Outside US Call to locate a distributor in your country.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.



Tech Spray, L.P. P.O. Box 949 Amarillo, TX 79105 www.techspray.com Aerosol MSDS
English
French
German
Italian
Spanish

Bulk MSDS
English
French
German
Italian
Spanish

