

**RTV Silicones**
[One Part](#)  
[Two Part](#)  
[Primers](#)  
**Selection Guides**
**ALL MG PRODUCTS ▾**
[Accessories](#)  
[Adhesives](#)  
[Brushes](#)  
[Cleaners / Degreasers](#)  
[Contact Cleaners](#)  
[Desoldering Braid](#)  
[Dusters & Circuit Coolers](#)  
[EMI / RFI Shielding](#)  
[Epoxies](#)  
[Flux and Flux Remover](#)  
[Glass & Screen Cleaners](#)  
[Lubricants](#)  
[Potting & Encapsulating](#)  
[Protective Coatings](#)  
[Pens](#)  
[Prototyping Materials](#)  
[RTV Silicones](#)  
[Specialized Cleaners](#)  
[Swabs](#)  
[Thermal Management](#)  
[Thermally Conductive Adhesives](#)  
[Wipes](#)

# RTV Silicones by

## 1-Part Adhesive Sealant RTV167

[▶ BUY NOW](#)
**Primary Characteristics**

- ▶ Light Gray Paste
- ▶ **High strength electronics**
- ▶ Non-corrosive
- ▶ Alkoxy neutral cure
- ▶ MIL-A-46146, group 1, type 1
- ▶ UL HB recognition
- ▶ UL File No. E36952

Excellent in areas that require an extra strength sealing and bonding. Non-corrosive to electronic metals, including copper and brass. Can be applied to vertical or overhead surfaces. Retains elastomeric properties for long periods at temperatures from -60°C to 205°C (75°F to 400°F) and for short periods up to 250°C (500°F). Excellent electrical insulating properties. This product meets Military spec. MIL-A-46146 and is UL HB recognized.

### Available Sizes

Catalog Number	Sizes Available	Description	Case Qty
RTV167-85ML	85 mL (2.8 oz)	Tube	12
RTV167-300ML <a href="#">▶ SPECIAL ORDER</a>	300mL (10 oz)	Cartridge	24

### Specifications

Use	Adhesive Sealant
Special Feature	High tensile strength
Standards	MIL-A-46146, group 1, type 1
	UL File no. E-36952
Cross Reference	RTV167
<b>Uncured Properties</b>	
Consistency	Paste
Color	Grey
Specific Gravity	1.12
Tack Free Time	4 hours
Cure through time	48 hours
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
<b>Cured Properties - MECHANICAL</b>	
Hardness	37 (Shore A)
Tensile Strength	5.49 MPa (800 psi)
Elongation	600%
Peel Strength	10 kg/cm
	80 lb/in
<b>Cured Properties - ELECTRICAL</b>	
Volume Resistivity	$3 \times 10^{15}$ ohm · cm

### Quick Links

- ▶ [MSDS](#)
- ▶ [Specifications](#)
- ▶ [Available Sizes](#)
- ▶ [Handling & Safety](#)
- ▶ [Application](#)
- ▶ [Surface Preparation](#)
- ▶ [Warranty](#)

**Related products:**

- RTV160 White
- RTV162 White
- TSE397C Clear
- TSE399C Clear

### Find by Product Number

[GO](#)

### Resources

- [What are RTV Silicones? ▶](#)
- [Application Guide ▶](#)
- [Product Data Spreadsheet ▶](#)

### Find by Application

- [General Purpose ▶](#)
- [Aerospace ▶](#)
- [Marine ▶](#)
- [High Performance Assembly ▶](#)
- [Electronics ▶](#)
- [Thermal Conductivity ▶](#)
- [High Temperature ▶](#)
- [Low Temperature ▶](#)



Dielectric Strength	19.7 kV/mm
	500 V/mil
Dielectric Constant	2.8 @ 60 Hz
<b>CURED PROPERTIES - THERMAL</b>	
Thermal Conductivity	0.21 W/m · °K
Brittle Point	-60°C (-75°F)
Thermal Expansion	27 x 10 <sup>-5</sup> (°C) <sup>-1</sup>
<b>OTHER</b>	
Viscosity (@ 25°C)	180 g/min

[Return to top ^](#)