

RTV Silicones

[One Part](#)
[Two Part](#)
[Primers](#)
[Selection Guides](#)

ALL MG PRODUCTS ▾

[Accessories](#)
[Adhesives](#)
[Brushes](#)
[Cleaners / Degreasers](#)
[Contact Cleaners](#)
[Desoldering Braid](#)
[Dusters & Circuit Coolers](#)
[EMI / RFI Shielding](#)
[Epoxies](#)
[Flux and Flux Remover](#)
[Glass & Screen Cleaners](#)
[Lubricants](#)
[Potting & Encapsulating](#)
[Protective Coatings](#)
[Pens](#)
[Prototyping Materials](#)
[RTV Silicones](#)
[Specialized Cleaners](#)
[Swabs](#)
[Thermal Management](#)
[Thermally Conductive](#)
[Adhesives](#)
[Wipes](#)

RTV Silicones by

2-Part Potting/Encapsulating Compound RTV31

[▶ SPECIAL ORDER](#)
[▶ BUY NOW](#)

Primary Characteristics

▶ Red pourable

▶ Condensation cure

▶ **Extreme high temp**

▶ Useful to 260°C

(500°F)

▶ **Primer required**

Use for:

▶ Potting surge protectors on telephone poles

▶ Potting industrial filters

▶ High temp. electrical potting applications

▶ Mechanical protection

silicone rubber compound for electrical potting and mechanical applications for high temperature resistance and low viscosity with variable work times and cure rates. Elastomeric properties range from -54°C to 260°C continuously, to 316°C for short periods. Requires [primer](#) for adhesion. The product comes complete with catalyst DBT. [Specialized catalysts](#) are available upon request.

Available Sizes

Catalog Number	Sizes Available	Description
RTV31-1P	1 pint	pail
RTV31-1G	1 gallon	pail
RTV31-5G	5 gallon	pail
RTV31 requires a primer. Visit our primer guide for details.		





Specifications

Use	Potting & Encapsulating
Special Feature	High Temperature
Cross Reference	RTV31
Uncured Properties	
Consistency	Flowable
Color	Red
Specific Gravity	1.42
Pot Life	2 hours
Cure Through Time	24 hours
Useful Temp. Range	-54°C to 260°C (-65°F to 500°F)
Cured Properties - MECHANICAL	
Hardness	54 (Shore A)
Tensile Strength	5.98 MPa (870 psi)
Elongation	170%
Cured Properties - ELECTRICAL	
Volume Resistivity	1.6 x 10 ¹⁴ ohm · cm
Dielectric Strength	17 kV/mm (430 V/mil)
Dielectric Constant	4.4 @ 1000Hz
Cured Properties - THERMAL	

Quick Links

- ▶ [MSDS](#)
- ▶ [Catalyst options/MSDS](#)
- ▶ [Primer options/MSDS](#)
- ▶ [Specifications](#)
- ▶ [Available Sizes](#)
- ▶ [Handling & Safety](#)
- ▶ [Application](#)
- ▶ [Surface Preparation](#)
- ▶ [Warranty](#)

Related Products:

-  [RTV60](#)
-  [RTV88](#)
-  [RTV560](#)
-  [RTV566](#)

Find by Product Number



Resources

[What are RTV Silicones? >](#)
[Application Guide >](#)
[Product Data Spreadsheet >](#)

Find by Application

[General Purpose >](#)
[Aerospace >](#)
[Marine >](#)
[High Performance Assembly >](#)
[Electronics >](#)
[Thermal Conductivity >](#)
[High Temperature >](#)
[Low Temperature >](#)


Thermal Conductivity	0.31 W/m · °K
Thermal Expansion	20 x 10 ⁻⁵ cm/cm °C
	(11 x 10 ⁻⁵ in/in °F)
Other	
Viscosity (@ 25°C)	25,000 cps
Mix ratio (by weight)	100:0.5

[Return to top](#) ^