

## RTV Silicones

[One Part](#)
[Two Part](#)
[Primers](#)
[Selection Guides](#)

## ALL MG PRODUCTS ▾

[Accessories](#)
[Adhesives](#)
[Brushes](#)
[Cleaners / Degreasers](#)
[Contact Cleaners](#)
[Desoldering Braid](#)
[Dusters & Circuit Coolers](#)
[EMI / RFI Shielding](#)
[Epoxies](#)
[Flux and Flux Remover](#)
[Glass & Screen Cleaners](#)
[Lubricants](#)
[Potting & Encapsulating](#)
[Protective Coatings](#)
[Pens](#)
[Prototyping Materials](#)
[RTV Silicones](#)
[Specialized Cleaners](#)
[Swabs](#)
[Thermal Management](#)
[Thermally Conductive](#)
[Adhesives](#)
[Wipes](#)

# RTV Silicones

## 2-Part Potting/Encapsulating Compound RTV88

[▶ STOCKED ITEM](#)
[▶ BUY NOW](#)

### Primary Characteristics

▶ Red spreadable

▶ Condensation cure

▶ **Extreme high temp**

▶ Useful to 260°C

(500°F)

▶ Primer required

### Use for:

▶ Aerospace applications such as potting, encapsulating, coating and cushioning

Excellent for potting and encapsulating electric motors, transformers, and surge protection. Can be used in aerospace applications such as sealing, bonding and quaking on vertical or overhead surfaces. Composition is free of solvents and solvent odour. Excellent retention of elastomeric properties at temperatures from -54°C to 260°C (-65°F to 500°F) continuously, and up to 316°C (600°F) for short periods of time. This two part silicone is supplied with a curing agent. Silicone [primer](#) is required. Cures at room temperature and has excellent adhesion qualities. The product comes complete with catalyst DBT. [Specialized catalysts](#) are available upon request.

## Available Sizes

Catalog Number	Sizes Available	Description
RTV88-1P	1 pint	pail
RTV88-1G	1 gallon	pail
RTV88-5G	<a href="#">▶ SPECIAL ORDER</a> 5 gallon	pail
RTV88 requires a primer. Visit our <a href="#">primer guide</a> for details.		





## Specifications

Use	Potting & Encapsulating
Special Feature	High Temperature
Cross Reference	RTV80
<b>Uncured Properties</b>	
Consistency	Spreadable
Color	Red
Specific Gravity	1.47
Pot Life	45 minutes
Cure Through Time	24 hours
Useful Temp. Range	-54°C to 260°C (-65°F to 500°F)
<b>Cured Properties - MECHANICAL</b>	
Hardness	58 (Shore A)
Tensile Strength	5.79 MPa (830 psi)
Elongation	120%

## Quick Links

- ▶ [MSDS](#)
- ▶ [Catalyst options/MSDS](#)
- ▶ [Primer options/MSDS](#)
- ▶ [Specifications](#)
- ▶ [Available Sizes](#)
- ▶ [Handling & Safety](#)
- ▶ [Application](#)
- ▶ [Surface Preparation](#)
- ▶ [Warranty](#)

### Related Products:

-  [RTV31](#)
-  [RTV60](#)
-  [RTV560](#)
-  [RTV566](#)

## Find by Product Number



## Resources

- [What are RTV Silicones? >](#)
- [Application Guide >](#)
- [Product Data Spreadsheet >](#)

## Find by Application

- [General Purpose >](#)
- [Aerospace >](#)
- [Marine >](#)
- [High Performance Assembly >](#)
- [Electronics >](#)
- [Thermal Conductivity >](#)
- [High Temperature >](#)
- [Low Temperature >](#)



Cured Properties - ELECTRICAL	
Volume Resistivity	2.8 x 10 <sup>14</sup> ohm · cm
Dielectric Strength	17.4 kV/mm (440 V/mil)
Dielectric Constant	4.3 @ 1000Hz
Cured Properties - THERMAL	
Thermal Conductivity	0.31 W/m · °K
Thermal Expansion	20 x 10 <sup>-5</sup> cm/cm °C
	(11 x 10 <sup>-5</sup> in/in °F)
Other	
Viscosity (@ 25°C)	880,000 cps
Mix ratio (by weight)	100:0.5

[Return to top](#) ^