

DATA SHEET

TX13/7.1/4.8 Ferrite toroids

Supersedes data of September 2004

2008 Sep 01



FERROXCUBE
A YAGEO COMPANY



Ferrite toroids

TX13/7.1/4.8

RING CORES (TOROIDS)

Effective core parameters


SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	2.40	mm^{-1}
V_e	effective volume	361	mm^3
l_e	effective length	29.5	mm
A_e	effective area	12.3	mm^2
m	mass of core	≈ 1.8	g

Coating

The cores are coated with epoxy, flame retardant in accordance with “UL 94V-0”; UL file number E 228348. The colour is white. Maximum operating temperature is 200 °C.

Isolation voltage

DC isolation voltage: 1500 V. Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A_L (nH)	μ_i	TYPE NUMBER
3D3 ^{sup}	$415 \pm 20\%$	≈ 750	TX13/7.1/4.8-3D3
3F3	$990 \pm 20\%$	≈ 1800	TX13/7.1/4.8-3F3
3C90	$1260 \pm 20\%$	≈ 2300	TX13/7.1/4.8-3C90
3C81	$1475 \pm 20\%$	≈ 2700	TX13/7.1/4.8-3C81
3E27	$2750 \pm 20\%$	≈ 5000	TX13/7.1/4.8-3E27
3E6 ^{des}	$5400 \pm 30\%$	≈ 10400	TX13/7.1/4.8-3E6

Properties of cores under power conditions

GRADE	B (mT) at	CORE LOSS (W) at		
	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C
3C81	≥ 320	≤ 0.08	—	—
3C90	≥ 320	≤ 0.036	≤ 0.036	—
3F3	≥ 320	—	≤ 0.04	≤ 0.07

Ferrite toroids

TX13/7.1/4.8

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

This datasheet has been downloaded from:

www.EEworld.com.cn

Free Download

Daily Updated Database

100% Free Datasheet Search Site

100% Free IC Replacement Search Site

Convenient Electronic Dictionary

Fast Search System

www.EEworld.com.cn