## DATA SHEET

# TX55/32/18 Ferrite toroids

Supersedes data of September 2004

2008 Sep 01





Ferrite toroids TX55/32/18

#### **RING CORES (TOROIDS)**

#### **Effective core parameters**

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.651	mm <sup>-1</sup>
V <sub>e</sub>	effective volume	26580	mm <sup>3</sup>
l <sub>e</sub>	effective length	132	mm
A <sub>e</sub>	effective area	202	mm <sup>2</sup>
m	mass of core	≈ 134	g

#### Coating


The cores are coated with epoxy, flame retardant in accordance with "UL 94V-0"; UL file number E 235873. The colour is white.

Maximum operating temperature is 200  $^{\circ}$ C.

#### Isolation voltage

DC isolation voltage: 2000 V.

Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



#### Ring core data

GRADE	A <sub>L</sub> (nH)	$\mu_{\mathbf{i}}$	TYPE NUMBER
4A11	1350 ± 25%	≈ 700 <sup>(1)</sup>	TX55/32/18-4A11
3C11	8300 ± 25%	≈ <b>4300</b>	TX55/32/18-3C11
3E25	10620 ± 25%	≈ 5500	TX55/32/18-3E25
3E27	$10620 \pm 25\%$	≈ 5500	TX55/32/18-3E27

1. Old permeability specification maintained.

2008 Sep 01

Ferrite toroids TX55/32/18

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

#### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

1751



### This datasheet has been downloaded from:

www.EEworld.com.cn

Free Download
Daily Updated Database
100% Free Datasheet Search Site
100% Free IC Replacement Search Site
Convenient Electronic Dictionary
Fast Search System

www.EEworld.com.cn